

Product Information

ROHACELL® S

Polymethacrylimide Foam, Self-Extinguishing

ROHACELL® S is a closed-cell rigid foam based on polymethacrylimide (PMI) chemistry, which does not contain any CFC's.

ROHACELL® S rigid foam is self-extinguishing and particularly suitable for applications in rail vehicle and watercraft construction, as well as in the aeronautic industry.

ROHACELL® S can be processed using prepregs and all common vacuum infusion methods, RTM, and VARTM; pressures of up to 0.35 MPa are permissible at a temperature of 130°C.

The thermo-formability of ROHACELL® provides a tremendous manufacturing advantage.

ROHACELL® S is also easy to shape by machining.

If required, ROHACELL® S can be supplied with a test certificate attesting compliance with various specifications:

- FAR 25.853 (a)(1)(i) AITM 2.0002 Small Burner Test vertical (60s)
- FAR 25.853 (a)(1)(ii) AITM 2.0002 Small Burner Test vertical (12s)
- FAR 25.853 (a)(1)(iv) AITM 2.0003 Small Burner Test horizontal (15s)
- FAR 25.853 (a)(1)(v) AITM 2.0003 Small Burner Test horizontal (15s)
- FAR 25.853 (d) AITM 2.0007 Determination of the specific optical smoke density of aircraft interior materials
- AITM 3.0005 Determination of gas components of smoke generated by aircraft interior materials

For further information, please contact our experts by phone +49 6151 18 1005 or e-mail rohacell@evonik.com

Properties of ROHACELL® S

Properties	Unit	ROHACELL® 51 S	ROHACELL® 71 S	ROHACELL® 110 S	Standard
Density	kg/m ³	52	75	110	ISO 845
	lbs./cu.ft.	3.25	4.68	6.87	ASTM D 1622
Compressive strength	MPa	0.7	1.5	2.8	ISO 844
	psi	101	217	406	ASTM D 1621
Tensile strength	MPa	1.1	1.9	3.2	ISO 527-2
	psi	159	275	464	ASTM D 638
Shear strength	MPa	0.6	1.2	2.2	DIN 53294
	psi	87	174	319	ASTM C 273
Elastic modulus	MPa	50	90	150	ISO 527-2
	psi	7,250	13,050	21,750	ASTM D 638
Shear modulus	MPa	20	34	55	DIN 53294
	psi	2,900	4,930	7,975	ASTM C 273
Strain at break	%	3.5	3.5	3.5	ISO 527-2
					ASTM D 638

Technical data of our products are typical values for the nominal density.

Fire behavior of ROHACELL® S

Properties	ROHACELL® 51 S	ROHACELL® 71 S	ROHACELL® 110 S	Standard
Fire behavior	Self-extinguishing			ASTM D 1692-59
	M1/F2	M2/F3		AFNOR NF 16-101
	23.8%	23.2%		ASTM D 2863 (LOI)
	V-2			UL 94

® = registered trademark

This information and all technical and other advice are based on Evonik's present knowledge and experience. However, Evonik assumes no liability for such information or advice, including the extent to which such information or advice may relate to third party intellectual property rights. Evonik reserves the right to make any changes to information or advice at any time, without prior or subsequent notice. Evonik disclaims all representations and warranties, whether express or implied, and shall have no liability for, merchantability of the product or its fitness for a particular purpose (even if Evonik is aware of such purpose), or otherwise. Evonik shall not be responsible for consequential, indirect or incidental damages (including loss of profits) of any kind. It is the customer's sole responsibility to arrange for inspection and testing of all products by qualified experts. Reference to trade names used by other companies is neither a recommendation, nor an endorsement of the corresponding product, and does not imply that similar products could not be used.