

## Product Information

# ROHACELL® A

### STRUCTURAL FOAM FOR AIRCRAFT APPLICATIONS

ROHACELL® A is closed-cell rigid foam based on polymethacrylimide (PMI) chemistry that is completely free of CFC's and engineered to meet the demanding requirements of the aerospace industry.

Stringent quality control supported by extensive testing documentation of ROHACELL® A has led to specification by major aircraft manufacturers for more than 40 years, including MIL, CMS and others.

### PROCESSING AND PRODUCTION

ROHACELL® A foam is suitable for both prepreg processing and vacuum infusion at temperatures up to 130 °C (266 °F) and pressures up to 0.3 MPa (45 psi).

Curing method options include autoclave, vacuum bagged, RTM, VARTM and press.

Using a ROHACELL® core makes it possible to produce sandwich components in a single step (co-curing), resulting in reduced overall production time.

### WEIGHT SAVINGS

When building composite sandwich components, lightweight ROHACELL® A has a closed cell structure that ensures the resin stays exactly where you want it – in the interface. This eliminates excess and unnecessary resin that adds undesirable weight to the finished part.

### THERMOFORMING AND SHAPING

ROHACELL® A can be easily thermoformed or CNC machined to meet customer requirements. High precision, pre-shaped and ready-to-use foam cores in complex or simple geometries can also be supplied by the ROHACELL® Shapes Department.

| Property                         | Test Method*            | Unit                                     | ROHACELL®<br>31 A | ROHACELL®<br>51 A | ROHACELL®<br>71 A |
|----------------------------------|-------------------------|--|-------------------|-------------------|-------------------|
| Density                          | ISO 845<br>ASTM D 1622  | kg/m <sup>3</sup><br>lbs/ft <sup>3</sup> | 32<br>2.00        | 52<br>3.25        | 75<br>4.68        |
| Compressive Strength             | ISO 844<br>ASTM D 1621  | MPa<br>psi                               | 0.4<br>58         | 0.9<br>130        | 1.5<br>217        |
| Tensile Strength                 | ISO 527-2<br>ASTM D 638 | MPa<br>psi                               | 1.0<br>145        | 1.9<br>275        | 2.8<br>406        |
| Tensile Modulus                  | ISO 527-2<br>ASTM D 638 | MPa<br>psi                               | 36<br>5,220       | 70<br>10,150      | 92<br>13,340      |
| Elongation at Break              | ISO 527-2<br>ASTM D 638 | %  | 3                 | 3                 | 3                 |
| Shear Strength                   | DIN 53294<br>ASTM C 273 | MPa<br>psi                               | 0.4<br>58         | 0.8<br>116        | 1.3<br>188        |
| Shear Modulus                    | DIN 53294<br>ASTM C 273 | MPa<br>psi                               | 13<br>1,890       | 19<br>2,755       | 29<br>4,205       |
| Coefficient of Thermal Expansion |                         | 1/K*10E-5                                | 3.70              | 3.33              | 3.52              |

Technical data values presented above are typical for nominal density, subject to normal manufacturing variations. \*Data values are based on ISO & DIN standard test methods, however ASTM values can be confirmed upon request. All ROHACELL® products are closed-cell rigid foams based on polymethacrylimide (PMI) chemistry and contain no CFC's.

**FOR MORE INFORMATION**

If you have questions or would like to discuss using **ROHACELL® A** in your application, we encourage you to talk with your local ROHACELL® representative.

Visit [www.rohacell.com](http://www.rohacell.com) to locate and directly connect with the contact in your region, by phone or email.

**Disclaimer**

ROHACELL® is a registered trademark of Evonik Industries and its subsidiaries.

This information and all technical and other advice are based on Evonik's present knowledge and experience. However, Evonik assumes no liability for such information or advice, including the extent to which such information or advice may relate to third party intellectual property rights. Evonik reserves the right to make any changes to information or advice at any time, without prior or subsequent notice. EVONIK DISCLAIMS ALL REPRESENTATIONS AND WARRANTIES, WHETHER EXPRESS OR IMPLIED, AND SHALL HAVE NO LIABILITY FOR, MERCHANTABILITY OF THE PRODUCT OR ITS FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE), OR OTHERWISE. EVONIK SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND. It is the customer's sole responsibility to arrange for inspection and testing of all products by qualified experts. Reference to trade names used by other companies is neither a recommendation, nor an endorsement of the corresponding product, and does not imply that similar products could not be used.

**Evonik Resource Efficiency GmbH**

High Performance Polymers  
Performance Foams  
64293 Darmstadt, Germany  
Phone +49 6151 18-1005

**Evonik Corporation**

Theodore, Alabama USA  
Phone +1 866 764-6235

**Evonik Specialty Chemicals (Shanghai) Co., Ltd.**

Shanghai, China  
Phone +86 21 6119 1544