

Product Information

ROHACELL® HERO

Innovative **ROHACELL® HERO** delivers the latest in materials technology for composite aircraft structures that are lightweight, durable over their lifetime and less expensive to produce.

It's the new standard in aircraft structural core material!

KEEPING IT LIGHT

Sandwich technology is an excellent way to reduce weight and thanks to its outstanding mechanical properties and low density, **ROHACELL® HERO** sandwich cores offer the most weight saving potential of all structural foams.

Featuring a closed cell structure, **ROHACELL® HERO** minimizes added weight by taking up resin only in the cut surface cells – resulting in a lighter finished part weight compared with traditional honeycomb structures.

LONG HAUL DURABILITY

Offering excellent elongation at break properties, **ROHACELL® HERO** remains robust and durable for the lifetime of the aircraft.

Surface impact damage is easily visible during inspections and rework/repair is simple since the core damage does not extend beyond the initial impact location and there is no water ingress as can occur with honeycomb core structures.

IT CAN TAKE THE HEAT

With heat resistance of up to 210 °C (428 °F), processing or curing temperatures can be increased higher than other core materials allow (e.g., typical cure cycle at 180 °C/356 °F with maximum pressure dependent upon density). This results in significant reductions in total cycle time and faster part manufacturing.

No other core material offers such ease of processing in a wide variety of processes, including autoclave, resin infusion, RTM and VARTM.

WE CAN HELP YOU SHAPE THE FUTURE

Let our Sandwich Technology Center supply you with finished, ready-to-use shaped **ROHACELL® HERO** parts. Your cores will be delivered ready for immediate use in your next processing step.

- Eliminate waste
- Reduce in-house production time
- Up to 30 % cost savings



ROHACELL® HERO IN FLIGHT

ROHACELL® HERO is a recommended grade for core material in sandwich structures for aircraft wings, landing gear doors, radomes, vertical and horizontal stabilizers, ailerons and other areas subject to surface impact damage.

Property	Test Method	Unit	ROHACELL® 51 HERO	ROHACELL® 71 HERO	ROHACELL® 110 HERO	ROHACELL® 200 HERO
Density	ISO 845	kg/m ³ lbs/ft ³	52 3.25	75 4.68	110 6.87	205 12.80
Compressive Strength	ISO 844	MPa psi	0.6 87	1.1 160	2.5 363	7.1 1,030
Compressive Modulus	ISO 844	MPa psi	32 4,640	48 6,960	83 12,000	180 26,100
Tensile Strength	ISO 527-2	MPa psi	2.6 377	4.1 595	6.3 914	12.3 1,780
Tensile Modulus	ISO 527-2	MPa psi	82 11,900	123 17,800	189 27,400	389 56,400
Elongation at Break	ISO 527-2	%	8	9.5	9.9	10.8
Shear Strength	DIN 53294	MPa psi	0.7 102	1.3 189	2.3 334	5.2 754
Shear Modulus	DIN 53294	MPa psi	22 3,190	28 4,060	50 7,250	109 15,800
Maximum Shear Strain	DIN 53294	%	7.0	7.2	7.2	7.2
Coefficient of Thermal Expansion		1/K*10E-5	3.76	3.77	3.72	4.26

Technical data values presented are typical for nominal density, subject to normal manufacturing variations. All ROHACELL® products are closed-cell rigid foams based on polymethacrylimide (PMI) chemistry and contain no CFC's.

Disclaimer

ROHACELL® is a registered trademark of Evonik Industries and its subsidiaries.

This information and all technical and other advice are based on Evonik's present knowledge and experience. However, Evonik assumes no liability for such information or advice, including the extent to which such information or advice may relate to third party intellectual property rights. Evonik reserves the right to make any changes to information or advice at any time, without prior or subsequent notice. EVONIK DISCLAIMS ALL REPRESENTATIONS AND WARRANTIES, WHETHER EXPRESS OR IMPLIED, AND SHALL HAVE NO LIABILITY FOR, MERCHANTABILITY OF THE PRODUCT OR ITS FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE), OR OTHERWISE. EVONIK SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND. It is the customer's sole responsibility to arrange for inspection and testing of all products by qualified experts. Reference to trade names used by other companies is neither a recommendation, nor an endorsement of the corresponding product, and does not imply that similar products could not be used.

Evonik Resource Efficiency GmbH

High Performance Polymers
Performance Foams
64293 Darmstadt, Germany
Phone +49 6151 18-1005

Evonik Foams Inc.

Theodore, Alabama USA
Phone +1 866 764-6235

Evonik Specialty Chemicals (Shanghai) Co., Ltd.

Shanghai, China
Phone +86 1391 6212034