

Product Information

ROHACELL® HF

STRUCTURAL FOAM FOR ANTENNA APPLICATIONS

ROHACELL® HF is a closed-cell rigid foam based on polymethacrylimide (PMI) chemistry that is completely free of CFC's. With its extremely low dielectric constants and particularly favorable transmission properties at high frequencies, **ROHACELL® HF** is ideal for use in antenna applications.

PROCESSING BENEFITS

Featuring an extremely fine closed-cell structure, the foam ensures minimal resin uptake and problem-free compatibility with metallic facing materials due to the absence of corrosive effects.

ROHACELL® HF foam is suitable for hand lay-up, prepreg processing and vacuum infusion at temperatures up to 130 °C (266 °F) and pressures up to 0.3 MPa (44 psi).

APPLICATIONS

From miniature antennas in cell phones to large fixed ship-based and stationary antenna structures, **ROHACELL® HF** is used worldwide. Other typical applications include usage as structural core for radomes and mammography plates.

THERMOFORMING AND SHAPING

ROHACELL® HF can be easily thermoformed or CNC machined to meet application requirements.

High precision, pre-shaped and ready-to-use foam cores in complex or simple geometries can be supplied by the ROHACELL® Shapes Department.

Property	Test Method	Unit	ROHACELL® 31 HF	ROHACELL® 51 HF	ROHACELL® 71 HF
Density	*	kg/m ³ lbs/ft ³	32 ± 7 2.00 ± 0.44	52 ± 12 3.25 ± 0.75	75 ± 15 4.68 ± 0.94
Compressive Strength	ISO 844	MPa psi	0.4 58	0.9 130	1.5 217
Tensile Strength	ISO 527-2	MPa psi	1.0 145	1.9 275	2.8 406
Tensile Modulus	ISO 527-2	MPa psi	36 5,220	70 10,150	92 13,340
Elongation at Break	ISO 527-2	%	3.5	4.0	4.5
Shear Strength	DIN 53294	MPa psi	0.4 58	0.8 116	1.3 188
Shear Modulus	DIN 53294	MPa psi	13 1,885	19 2,755	29 4,205
Coefficient of Thermal Expansion		1/K*10E-5	N/A	3.34	3.23

Technical data values presented are typical for nominal density, subject to normal manufacturing variations. All ROHACELL® products are closed-cell rigid foams based on polymethacrylimide (PMI) chemistry and contain no CFC's. * Density values are valid for full-size sheets with a minimum thickness of 10 mm (0.39 inch) only. Other density ranges are available upon request.

ELECTRICAL PROPERTIES OF ROHACELL® HF

Property	Frequency [GHz]	31 HF	51 HF	71 HF
Dielectric constants	2.5	1.050	1.057	1.075
	5.0	1.043	1.065	1.106
	10.0	1.046	1.067	1.093
	26.5	1.041	1.048	1.093
Loss tangent	2.5	<0.0002	<0.0002	<0.0002
	5.0	0.0016	0.0008	0.0016
	10.0	0.0017	0.0041	0.0038
	26.5	0.0106	0.0135	0.0155

FOR MORE INFORMATION

If you have questions or would like to discuss using **ROHACELL® HF** in your application, we encourage you to talk with your local ROHACELL® representative.

Visit www.rohacell.com to locate and directly connect with the contact in your region, by phone or email.

Disclaimer

ROHACELL® is a registered trademark of Evonik Industries and its subsidiaries.

This information and all technical and other advice are based on Evonik's present knowledge and experience. However, Evonik assumes no liability for such information or advice, including the extent to which such information or advice may relate to third party intellectual property rights. Evonik reserves the right to make any changes to information or advice at any time, without prior or subsequent notice. EVONIK DISCLAIMS ALL REPRESENTATIONS AND WARRANTIES, WHETHER EXPRESS OR IMPLIED, AND SHALL HAVE NO LIABILITY FOR, MERCHANTABILITY OF THE PRODUCT OR ITS FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE), OR OTHERWISE. EVONIK SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND. It is the customer's sole responsibility to arrange for inspection and testing of all products by qualified experts. Reference to trade names used by other companies is neither a recommendation, nor an endorsement of the corresponding product, and does not imply that similar products could not be used.

Evonik Resource Efficiency GmbH

High Performance Polymers
Performance Foams
64293 Darmstadt, Germany
Phone +49 6151 18-1005

Evonik Foams Inc.

Theodore, Alabama USA
Phone +1 866 764-6235

Evonik Specialty Chemicals (Shanghai) Co., Ltd.

Shanghai, China
Phone +86 1391 6212034