

Product Information

ROHACELL® XT

FOR THE MOST DEMANDING PROCESS CONDITIONS

ROHACELL® XT is a closed-cell rigid foam based on polymethacrylimide (PMI) chemistry that is completely free of CFC's and is engineered to meet extreme and demanding processing requirements.

PROCESSING AND PRODUCTION

Of all the ROHACELL® grades, it is the grade that is best suited to withstand the most demanding process conditions: curing temperatures of up to 180 °C (356 °F) and pressures as high as 0.45 MPa (65 psi).

After heat treatment, ROHACELL® XT-HT can even be used at temperatures of 190 °C (374 °F) and pressure of 0.7 MPa (102 psi) dependent upon density. Typical curing temperatures of BMI resin system of up to 210 °C (410 °F) can be applied in a pressureless post-cure process.

These extreme properties make ROHACELL® XT the ideal foam for use with BMI resins, among other materials.

ROHACELL® XT foam is suitable for autoclave technologies, vacuum infusion, RTM and VARTM processes.

THERMOFORMING AND SHAPING

ROHACELL® XT can be easily thermoformed or CNC machined to meet customer requirements, bringing tremendous manufacturing advantages.

High precision, pre-shaped and ready-to-use foam cores in complex or simple geometries can also be supplied by the ROHACELL® Shapes Department.

Property	Test Method	Unit	ROHACELL® 71 XT	ROHACELL® 110 XT
Density	ISO 845	kg/m ³ lbs/ft ³	75 4.68	110 6.87
Compressive Strength	ISO 844	MPa psi	1.7 246	3.6 522
Tensile Strength	ISO 527-2	MPa psi	2.2 319	3.7 536
Tensile Modulus	ISO 527-2	MPa psi	105 15,220	180 26,100
Elongation at Break	ISO 527-2	%	4	4
Shear Strength	DIN 53294	MPa psi	1.4 203	2.1 304
Shear Modulus	DIN 53294	MPa psi	42 6,090	63 9,135

Technical data values presented above are typical for nominal density at room temperature, subject to normal manufacturing variations. All ROHACELL® products are closed-cell rigid foams based on polymethacrylimide (PMI) chemistry and contain no CFCs.

FOR MORE INFORMATION

If you have questions or would like to discuss using **ROHACELL® XT** in your application, we encourage you to talk with your local ROHACELL® representative.

Visit www.rohacell.com to locate and directly connect with the contact in your region, by phone or email.

Disclaimer

ROHACELL® is a registered trademark of Evonik Industries and its subsidiaries.

This information and all technical and other advice are based on Evonik's present knowledge and experience. However, Evonik assumes no liability for such information or advice, including the extent to which such information or advice may relate to third party intellectual property rights. Evonik reserves the right to make any changes to information or advice at any time, without prior or subsequent notice. EVONIK DISCLAIMS ALL REPRESENTATIONS AND WARRANTIES, WHETHER EXPRESS OR IMPLIED, AND SHALL HAVE NO LIABILITY FOR, MERCHANTABILITY OF THE PRODUCT OR ITS FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE), OR OTHERWISE. EVONIK SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND. It is the customer's sole responsibility to arrange for inspection and testing of all products by qualified experts. Reference to trade names used by other companies is neither a recommendation, nor an endorsement of the corresponding product, and does not imply that similar products could not be used.

Evonik Resource Efficiency GmbH

High Performance Polymers
Performance Foams
64293 Darmstadt, Germany
Phone +49 6151 18-1005

Evonik Foams Inc.

Theodore, Alabama USA
Phone +1 866 764-6235

Evonik Specialty Chemicals (Shanghai) Co., Ltd.

Shanghai, China
Phone +86 1391 6212034