

ROHACELL® HERO



Innovative ROHACELL® HERO delivers the latest in materials technology for composite aircraft structures that are lightweight, durable over their lifetime and less expensive to produce.

It's the new standard in aircraft structural core material!

Keeping it light

Sandwich technology is an excellent way to reduce weight and thanks to its outstanding mechanical properties and low density, ROHACELL® HERO sandwich cores offer the most weight saving potential of all structural foams.

Featuring an entirely closed cell structure, ROHACELL® HERO minimizes added weight by taking up resin only in the cut surface cells – resulting in a lighter finished part weight compared with traditional honeycomb structures.

Long haul durability

Offering excellent elongation at break properties, ROHACELL® HERO remains robust and durable for the lifetime of the aircraft.

Surface impact damage is easily visible during inspections and rework/repair is simple since the core damage does not extend beyond the initial impact location and there is no water ingress as can occur with honeycomb core structures.

It can take the heat

With heat resistance of up to 220 °C (428 °F), processing or curing temperatures can be increased higher than other core materials allow (e.g., typical cure cycle at 180 °C/0.7 MPa ac-

ceptable). This results in significant reductions in total cycle time and faster part manufacturing.

No other core material offers such ease of processing in a wide variety of processes, including autoclave, resin infusion, RTM and VARTM.

We can help you shape the future

Let our Sandwich Technology Center supply you with finished, ready-to-use shaped ROHACELL® HERO parts. Your cores will be delivered ready for immediate use in your next processing step.

- Eliminate waste
- Reduce in-house production time
- Up to 30 % cost savings



ROHACELL® HERO in flight

ROHACELL® HERO is a recommended grade for core material in sandwich structures for aircraft wings, landing gear doors, radomes, vertical and horizontal stabilizers, ailerons and other areas subject to surface impact damage.

ROHACELL® HERO properties

Property	Test method	Unit	(Preliminary)				
			ROHACELL® 51 HERO	ROHACELL® 71 HERO	ROHACELL® 110 HERO	ROHACELL® 150 HERO	ROHACELL® 200 HERO
Density	ISO 845	kg/m ³	52	75	110	150	205
Tensile strength	ISO 527-2	MPa	2.6	4.1	6.3	8.8	12.3
Tensile modulus	ISO 527-2	MPa	82	123	189	269	389
Elongation at break	ISO 527-2	%	8	9.5	9.9	10.3	10.8
Compressive strength	ISO 844	MPa	0.6	1.1	2.5	4.3	7.1
Compressive modulus	ISO 844	MPa	32	48	83	124	180
Shear strength	ASTM C 273	MPa	0.7	1.3	2.3	3.5	5.2
Shear modulus	ASTM C 273	MPa	22	28	50	75	109
Maximum shear strain	ASTM C 273	%	7.0	7.2	7.2	7.2	7.2

Technical data values presented above are typical for nominal density, subject to normal manufacturing variations.

Values listed for ROHACELL® 51 HERO are Preliminary. Testing still in progress.

All ROHACELL® products are closed-cell rigid foams based on polymethacrylimide (PMI) chemistry and contain no CFC's.

ROHACELL® is a registered trademark of Evonik Industries and its subsidiaries

This information and all technical and other advice are based on Evonik's present knowledge and experience. However, Evonik assumes no liability for such information or advice, including the extent to which such information or advice may relate to third party intellectual property rights. Evonik reserves the right to make any changes to information or advice at any time, without prior or subsequent notice. EVONIK DISCLAIMS ALL REPRESENTATIONS AND WARRANTIES, WHETHER EXPRESS OR IMPLIED, AND SHALL HAVE NO LIABILITY FOR, MERCHANTABILITY OF THE PRODUCT OR ITS FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE), OR OTHERWISE. EVONIK SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND. It is the customer's sole responsibility to arrange for inspection and testing of all products by qualified experts. Reference to trade names used by other companies is neither a recommendation, nor an endorsement of the corresponding product, and does not imply that similar products could not be used.

Evonik Resource Efficiency GmbH
High Performance Polymers
64293 Darmstadt, Germany
Phone +49 6151 18-1005
E-mail rohacell@evonik.com
www.rohacell.com

Americas
Evonik Foams Inc.
Theodore, Alabama, USA
Phone +1 866 764-6235

Evonik Specialty Chemicals
(Shanghai) Co., Ltd.
Shanghai, China
Phone +86 1391 6212034